

Technische Information
Anwendungstabelle für nichtrostende und hitzebeständige Stähle nach DIN 17 440

Zusatzwerkstoff								
Grundwerkstoff	4316	4551	4430	4576	4370		4829	4842
1.4306	x	x	x	x	x		x	
1.4301	x	x	x	x	x		x	
1.4308	x	x	x	x	x		x	
1.4312	x	x	x	x	x		x	
G1.4308	x	x	x	x	x		x	
G1.4312	x	x	x	x	x		x	
1.4541	x	x	x	x	x		x	
1.4550	x	x	x	x	x		x	
G1.4552	x	x	x	x	x		x	
1.4401			x	x	x		x	
1.4408			x	x	x		x	
1.4410			x	x	x		x	
G1.4408			x	x	x		x	
G1.4410			x	x	x		x	
1.4404			x	x	x		x	
1.4552			x	x	x		x	
1.4571			x	x	x		x	
1.4580			x	x	x		x	
G1.4581			x	x	x		x	
1.4435			x	x				
1.4436			x	x				
1.4573			x	x				
1.4583			x	x				
1.4581			x	x				
1.4713		x					x	
1.4724							x	
1.4741							x	
1.4762								x
1.4821								x
1.4845								x
1.4772								x
1.4745								x
1.4776								x
1.4823								x
1.4837								x
1.4846								x
1.4848								x
1.4849								x
HI					x*			
HII					x*			
HII					x*			
17Mn4					x*			

*sowie miterfasste Werkstoffe nach VdTÜV-Merkblatt 1153